

| Outside Diameter | | Wall thickness mm | Test Pressure kg/cm ² |
|------------------|-------|-------------------|----------------------------------|
| inch | mm | | |
| 1/2 | 21,3 | 2,80 | 48 |
| 3/4 | 26,7 | 2,90 | 48 |
| 1 | 33,4 | 3,40 | 48 |
| 1 1/4 | 42,2 | 3,60 | 83 |
| 1 1/2 | 48,3 | 3,70 | 84 |
| 2 | 60,3 | 3,90 | 161 |
| 2 1/2 | 73,0 | 5,20 | 172 |
| 3 | 88,9 | 5,50 | 154 |
| 4 | 114,3 | 6,00 | 152 |
| 5 | 141,0 | 6,60 | 135 |
| 6 | 168,3 | 7,10 | 123 |
| 8 | 219,1 | 8,18 | 108 |
| 10 | 273,0 | 9,27 | 99 |
| 12 | 323,9 | 9,50 | 86 |